

Customer No. 25280

Case 5113B

Amendments To The Claims:

Kindly amend the claims in accordance with the following claim set.

Claims 1-87 (Canceled)

88. (Previously Presented): A carpet tile comprising a carpet layer and a backing attached thereto and having at least one layer comprised of compressible particles bonded together, wherein said layer comprised of compressible particles bonded together has an internal tear strength of at least 3 lbs, and wherein said carpet tile has an appearance retention rating of at least 4.0 after 4,000 cycles.

89. (Canceled)

90. (Original): The carpet tile as recited in claim 88, wherein the layer of compressible particles bonded together is a compressed particle foam and has a compressibility of less than 100% of the foam thickness at 40 psi.

91. (Canceled)

92. (Currently Amended): The carpet tile as recited in claim ~~91~~ 88, having an appearance retention rating of at least 3 after 12,000 cycles.

93. (Original): The carpet tile as recited in claim 88, wherein said layer comprised of compressible particles bonded together is at least one of a cut, slit and peeled foam.

Customer No. 25280

Case 5113B

94. (Previously Presented): The carpet tile as recited in claim 88, wherein said layer of compressible particles has a recycled content of at least 85%.
95. (Original): The carpet tile as recited in claim 88, wherein said layer comprised of compressible particles bonded together is an open celled foam comprised of open celled foam particles bonded together.
96. (Original): The carpet tile as recited in claim 95, wherein the open celled foam is comprised of foamed polyurethane.
97. (Original): The carpet tile as recited in claim 88, wherein said particles bonded together have an average uncompressed chip size of 25 mm or less.
98. (Currently Amended): The carpet tile as recited in claim 88, wherein said layer comprised of compressible particles bonded together has a density of [=] 25 lbs/ft³ or less.
99. (Previously Presented): The carpet tile as recited in claim 88, wherein said layer of compressible particles has a recycled content of at least 50%.
100. (Original): The carpet tile as recited in claim 88, having a hexapod rating >2.0 at 12,000 cycles.

Customer No. 25280

Case 5113B

101. (Original): The carpet tile as recited in claim 88, wherein said layer comprised of compressible particles bonded together is one layer of a hot melt laminated carpet backing.
102. (Original): The carpet tile as recited in Claim 88, wherein said layer comprised of compressible particles bonded together is one layer of a flame laminated carpet backing.
103. (Original): The carpet tile as recited in claim 88, having an initial Gmax of less than 125.
104. (Original): The carpet tile as recited in claim 88, having a cushion weight of less than 32 oz/yd² and an initial Gmax less than 125.
105. (Original): The carpet tile as recited in claim 88, wherein the layer of compressible particles bonded together has at least one of a honey-combed, reticulated, and skeletal open cell structure.
106. (Original): The carpet tile as recited in claim 88, wherein the layer of compressible particles bonded together has a structure of randomly placed particles bonded together in a compressed state.
107. (Original): The carpet tile as recited in claim 88, wherein said layer of compressible particles bonded together is substantially free of any filler.
108. (Original): The carpet tile as recited in claim 88, wherein said compressible particles of said layer of compressible particles bonded together are substantially 100% recycled content.
109. (Original): The carpet tile as recited in claim 88, wherein the compressible particles are bonded together with an adhesive.

Customer No. 25280

Case 5113B

110. (Original): The carpet tile as recited in claim 109, wherein said adhesive contains at least one additive, agent or compound selected from flame retardant, anti-bacterial, color, anti-microbial, anti-fungal, conductive, anti-static, fibers, filler, recycled materials, and combinations thereof.
111. (Original): The carpet tile as recited in claim 88, wherein the compressible particles are bonded together in a compressed state.
112. (Original): The carpet tile as recited in claim 88, wherein said tile includes a plurality of layers of compressible particles bonded together.
113. (Original): The carpet tile as recited in claim 88, wherein said layer of compressible particles bonded together has at least one lateral surface which is cut, peeled, or slit.
114. (Original): The carpet tile as recited in claim 88, wherein the carpet layer includes at least one of woven, tufted, or bonded carpet.
115. (Original): The carpet tile as recited in claim 88, wherein said layer of compressible particles bonded together has air permeability.
116. (Original): The carpet tile as recited in claim 88, wherein the backing is a multilayer backing.
117. (Original): The carpet tile as recited in claim 88, wherein the backing includes a stabilizing layer.
118. (Previously Presented): The carpet tile as recited in claim 88, wherein the layer of compressible particles has a thickness of less than 8 mm.
119. (Original): The carpet tile as recited in claim 88, wherein the tile has an overall height of less than 10 mm.

Customer No. 25280

Case 5113B

120. (Previously Presented): A carpet tile comprising a carpet layer and a backing attached thereto and having at least one layer comprised of compressible particles bonded together, wherein said layer comprised of compressible particles bonded together has an internal tear strength of at least 3 lbs and wherein said carpet tile has a caster chair rating of >2.3.

121. (Previously Presented): A carpet tile comprising a carpet layer and a backing attached thereto and having at least one layer comprised of compressible foam particles bonded together, wherein said layer comprised of compressible foam particles bonded together has an internal tear strength of at least 3 lbs and wherein said carpet tile has an EN 1307 rating of >2.

122. (Previously Presented): A carpet tile comprising a carpet layer and a backing attached thereto and having at least one layer comprised of compressible foam particles bonded together, wherein said layer comprised of compressible foam particles bonded together has an internal tear strength of at least 3 lbs and wherein said carpet tile has a Herzog walking comfort rating for contract use (DIN 54327) of >0.70.

123. (Currently Amended): A cushion back carpet tile comprising a carpet layer and a cushion back attached thereto and having at least one layer comprised of preformed foamed polyurethane particles bonded together, wherein said layer comprised of foamed polyurethane particles bonded together has an internal tear strength of at least 3 lbs.

124. (Canceled)

125. (Original): The cushion back carpet tile as recited in claim 123, wherein said layer comprised of foamed polyurethane particles bonded together has a thickness of about 2 to 20 mm.

126. (Original): The cushion back carpet tile as recited in claim 123, wherein said layer comprised of foamed polyurethane particles bonded together has a compressibility of less than

Customer No. 25280

Case 5113B

100% at 40 psi.

127. (Original): The cushion back carpet tile as recited in claim 123, wherein said tile has an appearance retention rating of at least 4 at 4,000 cycles.

128. (Original): The cushion back carpet tile as recited in claim 123, wherein said tile has an appearance retention rating of at least 3 at 12,000 cycles.

Claims 129. - 130. (Canceled)

131. (Currently Amended): The ~~foam-backed~~ carpet tile as recited in of claim ~~130~~ 88, wherein said compressible particles have with an average uncompressed particle size of 15 mm or less.

Claims 132. - 148. (Canceled)

149. (Previously Presented): The carpet tile as recited in claim 111, wherein the layer of compressible particles is a rebond foam.